

**ENEOS USA Inc.**

[E-ne-o-s]

20 N. Martingale Rd, Suite 325, Schaumburg, IL 60173

CERTIFICATE OF ANALYSIS

Product Name	SP-CVT1
Manufacture Date	9/15/2026
Lot/Batch Number	NL26J037

TEST	METHOD	SPECIFICATION	RESULTS	UNITS
Appearance	Visual	Clear	Clear	
Color, (ASTM)	ASTM D1500	Report	L1.5	
Density, 15°C	ASTM D4052	0.82 - 0.88	0.85	g/cm ³
Flash Point, COC	ASTM D92	≥ 180	205	°C
Kinematic Viscosity, 40°C	ASTM D445	≤ 26	26	mm ² /s
Kinematic Viscosity, 100°C	ASTM D445	5.3 - 5.5	5.4	mm ² /s
Viscosity Index	ASTM D2270	≥ 150	155	
Brookfield Viscosity, -40°C	ASTM 2983	≤ 10,000	7,465	mPa·s
Pour Point	ASTM D97	≤ -40.0	-54	°C
TAN	ASTM D664	Report	1.21	mgKOH/g
TBN - HClO ₄	ASTM D2896	Report	4.42	mgKOH/g
Aniline	ASTM D611	≥ 100	114.05	°C
Copper Corrosion, 100°C @ 3 Hr	ASTM D130	≤ 1	1A	
Foaming SEQ I	ASTM D892	Report	0 / 0	mL/ml
Foaming SEQ II	ASTM D892	Report	0 / 0	mL/ml
Foaming SEQ III	ASTM D892	Report	0 / 0	mL/ml
Elemental Analysis - B	ASTM D4951	Report	344	mass ppm
Elemental Analysis - Ca	ASTM D4951	Report	550	mass ppm
Elemental Analysis - P	ASTM D4951	Report	551	mass ppm
Elemental Analysis - S	ASTM D4951	Report	0.10	mass %
Elemental Analysis - Zn	ASTM D4951	Report	3	mass ppm
Elemental Analysis - N	ASTM D4629	Report	0.14	mass%
Water Content, (KF)	ASTM D6304	Report	80	ppm

Joy Rogers
General Manager, Quality Control Group

FM-QC-261
Rev. 1
04/16/18