CERTIFICATE OF ANALYSIS

ENEOS

Product Name ENEOS Full Synthetic 0W20 SQ GF-7A dexos1gen3
Lot Number NL26K052
Date of Manufacture 10/15/2026

TEST ITEM	METHOD	SPECIFICATION MIN	SPECIFICATION MAX	RESULTS	UNITS
Appearance	Visual	C & B	--	C & B	--
Density 15°C	ASTM D4052	Report	--	0.8455	g/cm3
Kinematic Viscosity, 40°C	ASTM D445	Report	--	45.17	mm2/s
Kinematic Viscosity, 100°C	ASTM D445	7.962	< 9.300	8.525	mm2/s
Viscosity Index	ASTM D2270	Report	--	169	--
CCS Viscosity, -35°C	ASTM D5293	--	6,200	5,851	mPa·s
Pour Point	ASTM D5950	--	-42	-45	°C
Foaming Tendency Seq. II	ASTM D892 IP 146	--	50	0	ml
Foaming Stability Seq. II	ASTM D892 IP 146	--	0	0	ml
Elemental Analysis - Ca	ASTM D4951	0.130	0.160	0.155	mass%
Elemental Analysis - P	ASTM D4951	0.0674	0.0849	0.0792	mass%
Elemental Analysis - Zn	ASTM D4951	0.0779	0.116	0.0933	mass%
*1 TBN (HClO4)	ASTM D2896	Report	--	9.02	mgKOH/g
*2 MRV Viscosity, -40°C	ASTM D4684 (A)	--	40,000	21,688	mPa・s
*2 MRV Yield Stress	ASTM D4684 (A)	--	y ≤ 35	y ≤ 35	--

Notes
*1 This property is measured at 3 month intervals, and the most recent measured value is shown here.
*2 This property is measured at 6 month intervals, and the most recent measured value is shown here.

ENEOS USA Inc.
[E-ne-ohs]
20 N. Martingale Rd, Suite 325, Schaumburg, IL 60173

Joy Rogers

Joy Rogers, General Manager Quality Control